

LAVAREP F60

High Strength Fiber Reinforced **Concrete Repair Mortar**

Description:

LAVAREP F60 is a premixed, cementitious, fiber reinforced, polymer modified, shrinkage compensated repairing mortar. It is composed of high resistance hydraulic binders, silica sand graded aggregates, special additives and reinforcing fiber to perform batching repairs with high compressive strength. It is supplied in ready to use blended powder which requires only addition of water to produce workable, thixotropic, non-sagging repair mortar for vertical and overhead applications.

Applications:

LAVAREP F60 is suitable for wide range of concrete and cement surface batching repair, including:

- General repair of concrete structures of shear walls, slabs and columns.
- Vertical and overhead repair.
- Repair of expansion joints.
- Precast concrete repairs.
- General repair of degraded concrete structural elements.
- Honeycombing repair in reinforced concrete elements
- Edges of beams, pillars, risers of balconies, terraces
- Bridges, dams, tunnels, channels and concrete pavements

Advantages:

- Single component, requires addition of water only.
- Excellent bond to all concrete substrates.
- Can be applied on vertical, overhead or horizontal places without the use of formwork.
- Shrinkage compensated-reduces the risk of cracking
- High compressive strength and impact resistant of finished layer.
- High build achievable with excellent mechanical strength.
- Excellent workability and thixotropic mortar.
- Low permeability provides protection against chloride, atmosphere gases and salts penetration.

- Re-coatable and compatible with other cement products

Instructions for Use:

Surface Preparation:

In concrete repairs, proper surface preparation is essential for obtaining good results. Mark the boundary of the damaged areas of concrete and then cut neatly by saw cutting machine or disc grinder to a depth of 10mm. Then chip the concrete within the boundary down to sound base using sharp tools or chipping hammer all corroded steel should be completely exposed including the rear side of the bar to enable thorough cleaning. In case that reinforcing bars section is reduced due to oxidization, integrate them with additional bar reinforcement.

The concrete substrate should be clean from all grease, contaminants, oil and loose material. After completing the chipping, clean the surface with steel brush. In case of deep rusting or contamination, it is recommended to clean using sand blasting to reinforcing steel. Particular attention should be paid to the rear of the bar to ensure all corrosion products have been removed. Once the reinforcing steel has been cleaned it should be coated immediately with one coat of LAVAZINC EP or LAVAFER.

Before applying LAVAREP F60, soak the substrate with water. Allow excess water to drain or to evaporate. Ensure a saturated surface dry condition "SSD" prior to application of repair mortar.

For superior bonding strength with the substrate, apply a coat of MEGABOND SBR slurry as a bonding coat primer before applying the repair mortar. Application of repair mortars over dry concrete surfaces without saturation with clean water "SSD" or priming with a bonding agent will result in failure of product and defect in repair.

Mixing:

To prepare the mortar, pour 4.0 to 4.5 liters of clean water into container and add slowly the LAVAREP F60 powder bag contents (25 Kg). Mix using spiral

LAVAREP F60

paddle fitted to slow speed heavy duty drill for few minutes till a homogeneous lump free consistency mix is achieved.

Always add powder to water and not water to powder. Avoid adding thinning water after the mixture is homogenous and ready for use.

Application:

Apply LAVAREP F60 manually with a trowel or spatula to the saturated surface of concrete "SSD". For vertical surfaces applications, the minimum applicable layer thickness is around 10 mm and can reach up to a maximum is 35 mm. On horizontal surfaces, repair thickness can reach up to 100 mm per layer. For vertical application, if the application of a second layer is necessary to reach higher thicknesses, the first layer must be applied with proper pushing then roughened to increase bonding with the second layer.

For large repair areas, LAVAREP F60 can be sprayed by a mortar spray machine. Ensure proper mix of gauging water and apply a sample area to ensure mixture consistency and bonding prior to full application.

Curing cementitious repair products is essential. It is essential to follow good concrete curing practice and to protect the repaired area from drying winds, sun or excessive heat to avoid rapid evaporation of mix water in the applied mortar. Cover the area with wet hessian cloth covered with polyethylene sheet for two days. A coat of a recommended MATEX curing agent could be applied instead. Consult with MATEX Technical Department for further instructions.

Standards:

LAVAREP F60 conforms to:

- BS 1881, Part 116, BS 6319
- UNI 6556, UNI 9532, UNI - EN 196
- ASTM C 157 - 93
- DIN 1048

Cleaning:

Clean tools with water prior to product hardening.

Coverage:

LAVAREP F60 achieves coverage of 16 kg/square meter @ 10 mm thickness.

TECHNICAL PROPERTIES	
Appearance	: Cement Grey
Dry Density	: 2.1 kg/ Lt.
Wet Density	: 2.25 kg/ Lt
Aggregate Size	: Up to 2.0 mm
Temp. of application	: From +5°C to +35°C
Adhesion bond to concrete	: 1.8 N/mm2
Water Absorption	: <2.0%
Pot-life-time of mixture	: 35 minutes @ 25°C
Compressive strength	: 40 N/mm ² @ 7 days
	: 63 N/mm ² @ 28 days
Flexural Strength	: 8.0 N/mm ² @ 28 days
Thickness per Coat	: 10–35 mm vertical
	: 10–25 mm overhead
	: 10–100 horizontal

Packaging:

LAVAREP F60 is supplied in 25 kg high quality recyclable paper bags.

Storage Conditions:

Store in original packing in dry conditions away from direct sunlight and high humidity levels.

Shelf Life:

LAVAREP F60 can be utilized within 12 months of production date if stored in proper conditions in unopened original packing.

Health and Safety:

- Use goggles and gloves during application. Do not breathe vapor of products. Use only in well ventilated areas.
- Avoid contact with eyes or skin.

MATEX Rev.00-1015

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.

