

PLASTOMIX C200 S

High Strength Cementitious Dry **Ready Mix Plaster**

Description:

PLASTOMIX C200 S is a high strength cement based ready mix plaster. Formulated for exterior and interior plastering work to give a hard, smooth, and good shrinkage control layer. It is composed of Portland cement, lime, graded aggregates, polymers and chemical additives to give when mixed with water, high workable, homogeneous good adhesion mix. PLASTOMIX 200 S can be applied traditionally by hand or by using plaster-spraying machine.

Applications:

PLASTOMIX C200 S is recommended for plastering on block walls, ceilings, bricks and concrete surfaces, but should not be applied on painted surfaces. For the application on AAC lightweight blocks, fair face concrete or concrete containing micro silica, use appropriate type of RUSHBOND spatter key coat to provide mechanical bonding.

Advantages:

- Easy to mix and apply, just add water.
- Pre-packed in the factory.
- Ideal for internal and external application.
- Low shrinkage.
- Good strength.
- High durability.
- Suitable for hot water.

Instructions for Use:

Surface Preparation:

The substrate should be free of loose particles, dust, dirt, grease, oil, curing agents or paint. Absorbent and porous substrates should be moistened with water prior to the application of PLASTOMIX C200 S.

It is always required to apply RUSHBOND, a spatter dash coat, on the substrate before applying PLASTOMIX C200 S to improve adhesion and high bonding with the substrates. The right type of RUSHBOND applied

depends on the substrate. For normal fair face concrete use RUSHBOND, for AAC lightweight block surface use RUSHBOND LB, and for concrete containing micro silica, GGBS, gypsum or cement boards or polystyrene surfaces, use RUSHBOND MS. Contact MATEX Technical Department for assistance.

Concrete or blocks substrates should have been allowed to cure sufficiently. All shrinkage movements should take place before applying PLASTOMIX C200 S. Do not apply PLASTOMIX C200 S on surface exposed to movement, vibration or mechanical impacts. Saturate the surface with water and wait for the evaporation of excess water before applying the mix.

Mixing:

Add PLASTOMIX C200 S bag of 50 kg into a container of 8-9 liter of clean water. Mix until a uniform lumps free consistency mix achieved. Leave the mix to stand for 5 minutes and remix before uses. Use low speed mechanical mixer (200-300 rpm) fitted with a suitable mixing paddle. The mixture remains workable for one hour after mixing at 25°C. In case of application by using spray machine, adjust the water level to get suitable mix viscosity with uniform consistency.

Application:

PLASTOMIX C200 S can be applied manually or by using spray machine direct in one coat of a thickness of up to 20mm. If higher thickness is required than apply the mortar in two layers. The first layer should be finished with a rough texture to provide mechanical Key with the second layer. Cure the first layer with clean water for two days before applying the second coat. The total thickness should not be more than 40 mm.

Once the plaster starts to set, smooth/even the applied plaster manually by using wood/plastic float and steel trowel. Do not spray water on the applied coat to ease the finishing process. Such wrong practice allows the cement content to be removed which will weaken the compressive strength of the plaster surface. Plaster should be sufficiently cured with water. In order to ensure proper curing, it is advisable to keep the

PLASTOMIX C200 S

plastered surface moist and protected from sun and wind during the first 48 hours.

Remarks:

- Do not apply PLASTOMIX C200 S in rainy weather.
- During summer season, working area should be covered to prevent the direct sun effect. Keep equipment in shaded area and use cold water for mixing.
- Saturate the substrates with clean water before applying PLASTOMIX C200 S.
- After application, plaster should be cured for minimum two days.
- No further water should be added to the mix. Hard and set plaster should not be re-mixed or used.
- Do not apply PLASTOMIX C200 S onto gypsum, metallic, wooden supports or painted surfaces.
- Before applying any kind of stucco finish, paint, or wall paper the plaster has to be allowed to dry out completely.

Standards:

PLASTOMIX C200 S conforms to:

- ASTM C150, ASTM C926, ASTM C897,
- BS 1015, BS 4551

Packaging:

PLASTOMIX C200 S is available in 50 kg bags.

Coverage:

PLASTOMIX C200 S will require 16.0 kg to cover 1.0 square meter @ 10 mm thickness.

Storage:

Store PLASTOMIX C200 S in dry and covered area away from direct sun light in a dry place. Keep material protected from rainfall and avoid excess compaction.

TECHNICAL PROPERTIES

Appearance	:	Cementitious Powder
Wet Density	:	1,780 (kg/m ³)
Workability Time	:	40 minutes @ 25°C
Aggregate Size	:	Up to 2.0 mm
Compressive Strength	:	20.0 N/mm ² @28 days
Flexural Strength	:	2.0 N/mm ² @ 28 days
Curing	:	With water for minimum two days
Dry Density	:	1.75 g/cm ³ at 20°C
Grain Size	:	Up to 2.5 mm
Pull Out Strength	:	< 0.5 N/mm ²
Adhesion with RUSHBOND MS	:	1.5 N / mm ²
Consumption	:	Approximately 16-17 Kg. per m ² for 10 mm thickness

Shelf Life:

Shelf life is 12 months in original unopened bag when the above conditions are met.

Cleaning:

Clean used tools with water before the product dries.

Health and Safety:

- Use goggles and gloves during application. Do not breathe dust of product.
- Avoid contact with eyes or skin.
- In case of eye contact, flush thoroughly with plenty of water and seek immediate medical help.

MATEX Rev.00-1015

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.

