

EPOSHIELD EPP

Two Part Elastomeric Epoxy-polysulfide Coating

Description:

EPOSHIELD EPP is a high build elastomeric two component liquid applied protective coating membrane based on epoxy resins modified with Polysulfide resins for high elasticity and high durability features. EPOSHIELD EPP has excellent adhesion to most substrates including concrete, plaster, masonry, and metal surfaces.

EPOSHIELD EPP cures to form highly dense seamless continuous monolithic membrane that has excellent adhesion to most substrates. The cured membrane has high flexibility and high resistance to chemicals. It is specifically developed as lining and waterproofing coating for potable water retaining structures and as a superior chemical resistance flexible protective coating for industrial structures. Its flexibility and ease of application also make it ideal for use as crack sealing coating.

Applications:

- Internal water proofing membrane for water tanks, concrete or steel.
- Wet areas, showers, bathrooms, kitchens, balconies, planters, pools, especially in public used utilities.
- Water proofing at meat and poultry factories.
- Water proofing membrane at food processing areas.
- Swimming pools and water parks waterproofing, where high features of waterproofing membrane are required.
- Hard wearing and chemically resistant floor coating in industrial areas.
- Heavy duty protective coating for concrete and steel in oil refineries, paper mills, garages, hospitals, hangers, man holes, sewage water tanks and most liquid containment areas

Advantages:

- High build liquid applied membrane in single application.
- Fast drying chemically cured product.
- Nontoxic, low odor.
- Highly flexible to be applied where movement is expected.
- Self-priming, requires no primer to adhere to substrate.
- Crack bridging ability, can serve as waterproofing membrane in car park systems.
- Chemical resistant to detergents, cleaning materials, brackish water and salt water.

Instructions for Use:

Surface Preparation:

All surfaces should be sound, clean, dry and free from loose material, efflorescence, laitance, curing compounds; dirt, oil and grease. Ensure that concrete surfaces are cured for at least 28 days old and have moisture content not exceeding 5%. Old or existing floor should be refurbished mechanically to ensure clear sound substrate. Mechanical methods like grinding or grit/captive blasting in order to provide a suitable profiled open textured surface is strongly recommended.

Surface irregularities, cracks and blow holes shall be repaired with LAVAPOXY range of products. Cracks, expansion joint and control joints should be properly addressed, prior to application. After all preparation is complete, ensure dust is removed from the surface using an industrial vacuum. Apply injection material for penetrating cracks to ensure structurally sound containment before applying EPOSHIELD EPP membrane. Steel Surfaces should be grit blasted to surface quality SA 2 1/2. Coat the surface before it starts to re-oxidize.

Apply a rich coat of primer ARMOPRIME EP100, a solvent free epoxy primer, to the surface in a spread rate of rate

EPOSHIELD EPP

of 4 to 6 m²/Lt. Refer to the relevant data sheet for the recommended method application Of mixing and applying the primer. Allow the primer to be tack free before over coating with EPOSHIELD EPP.

Mixing:

EPOSHIELD EPP is supplied in two pre-weighted components kit. Thoroughly stir the contents of the base and hardener separately. Pour component B hardener into the pail of Component A base and mix well with a heavy duty mixer fitted with a proper paddle operated at low speed till a homogenous mix is reached. Scrape the side of the pail to ensure the entire product has been properly mixed. Leave the mixed material for a period of 2 minutes to release entrapped air from the mix.

Application:

Apply EPOSHIELD EPP uniformly over primed surfaces with a roller, trowel, brush or spray machine. It is recommended to apply two coats with a minimum total dry film thickness of 500 micron to achieve the best results of product. Apply a rich coat to the surface in a spread rate of 4 square meters/liter/coat. Second coats can be applied with same rate of application preferably in 90 degree direction.

EPOSHIELD EPP should not be applied on surfaces with a risk of rising dampness and should not be applied at temperature below 5°C. Water test should be executed after 14 days of material application to allow the membrane to be fully cured.

If the product will be totally exposed to sun and atmosphere, apply a top coat of ARMOFLOOR UVR or ARMOGUARD UV, a UV protective polyurethane coating layer. While applying the product in wet areas, it is recommended to pay extra attention to penetrations. An additional strip of product to be applied around penetrations such as pipes and conduits to ensure proper sealing and waterproofing features. Tiles can be applied once the membrane totally cures.

For park decking system, EPOSHIELD EPP can be applied as a flexible crack bridging wear coat with an anti-slip finish. Broadcast quartz on the first coat while it is still wet and allowed to dry completely. After overnight drying, the excess quartz can be brushed away and the second coat can be applied.

If EPOSHIELD EPP is applied as a membrane liner in water tanks, no further coating is required, as it is a non-toxic membrane and the membrane can contain potable water. Expansion joints in water tanks should be treated with MEGASEAL PU sealant. Use HYDROJOINT TAPE on the sealed expansion joints, around pipe through penetrations and to corner angles of the water tanks, to ensure a water tight system.

Standards:

EPOSHIELD EPP conforms to:

- ASTM D2240, ASTM C 501, ASTM D412, and ASTM D624

TECHNICAL PROPERTIES

Color	:	Grey, white and light blue
Density	:	1.50 Kg. / cm ³
Solid Contents	:	100%
Pot life at 25°C	:	50 minutes
Touch Dry	:	6 hours
Full Dry	:	7 hours
Adhesion to concrete	:	2.0 N/mm ² or concrete failure
Shore A hardness (after 7 days)	:	40
Crack bridging	:	Up to ¼ inch ,no effect
Tensile strength (after 7 days)	:	12.0 N / mm ²
Elongation at Break	:	Above 70 %
Service Temperature	:	-5°C to +80°C
Adhesion to concrete	:	Concrete Failure
Application Temp.	:	+5°C to + 40°C
Water penetration	:	NIL
Chemical Properties	:	
Acidic solutions	:	Resistant
Alkali solutions	:	Resistant
Sea, brackish water	:	Resistant
Oil and grease	:	Resistant
Detergents	:	Resistant
Thinners and solvents	:	Moderate resistance

Packaging:

EPOSHIELD EPP is available in a set of 4 and 15 liter supplied in metallic dual pack.

EPOSHIELD EPP

Storage:

Store in original packing in dry conditions away from direct sunlight and in a shaded warehouse.

Coverage:

EPOSHIELD EPP achieves coverage of 2 square meter/liter @ 500 micron dry film thickness.

Shelf Life:

EPOSHIELD EPP can be utilized within 12 months of production date if stored in proper conditions in unopened original packing.

Cleaning:

All tools and equipment should be cleaned immediately after use with MATEX SOLVENT.

Health and Safety:

- Use goggles and gloves during application. Do not breathe vapor of products. Use only in well ventilated areas.
- Avoid contact with eyes or skin.

MATEX Rev.00-1015

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.



P.O. BOX: 29585, Dubai, UAE, Tel: +971 4 333 4140, Fax: +971 4 333 4115
Email: info@matex.ae, www.matex-global.com