



Elastoguard Paint

6502

PRODUCT DESCRIPTION

An super quality two pack elastomeric waterproofing coating based on plasticized acrylic resin and some special pigments . It has prolong durability as an water proofing coating for the protection of water leakage.

PRODUCT USE

For exterior use only .
 Good weather resistant.
 Good adhesion properties.
 Provide a seamless elastoguard membrane to prevent water leakage.
 Non- toxic.
 Non-yellowing.
 Water vapor permeable.
 Can work at a variety of temperatures.
 Almost odourless and easy to apply.

SUBSTRATES

Bathroom, kitchen, tank , pool,walls of concrete, tiles, masonry, cement rendering and plasters e

CHARACTERSTICS

Color	White or any requested color
Finish	Smooth/ Flat
Gloss	Matt
Density gm/cc	1.48 +/- 0.02
Volume Solids %	46
Theoretical Coverage	Approx. 1-2 sq. mt/lt.(depends upon the substrate condition & method of application)
Mixing Ratio	1:1 by weight.
Drying Time (S/D)	Approx 1-2 hours.
Drying Time (H/D)	4 hours.(min.)
Washability	Above 1500 cycles.
Adhesion of Paint Film	Satisfactory
Flexibility of Paint Film	Excellent.
Flash Point	NA
Pot Life	60--90 mints
Overcoat Interval	Approx. 6 hours.
Shelf Life	12 months from date of production.

SURFACE PREPARATION & CONDITION

Should be stable , firm, dry and free from laitance,dust and loose flaking materials,loose old paints, dirt, grease, wax and any other contaminations.



Elastoguard Paint

6502

PAINT SYSTEM ADVICES

a) For New Sustrates

Ensure cement based and plastered surfaces are dry enough and properly cleaned.
Concrete : Surface should be cleaned by sand blasting or by acid etching. If acid etching is used, surface should be thoroughly washed, afterwards wash with clean water to remove any residue then allowed to dry below 12% moisture content. Any defects should be filled with suitable repair mortar if greater than 3 mm in depth.

b) Old Sustrates

Plywood : All seams must be reinforced by embedding a 10 cm. wide strip of fiberglass tape into the wet elastoguard which then should be brushed evenly over the seam to a WFT of approx. 500 micron.
the application of water proof can be subsequently be made over the entire surface including the

APPLICATION DETAILS

Porous and slightly textured areas should be primed first with a coat of Elastoguard paint diluted with 20% water maintaining a thickness of 100-150 micron.
At intersections of membrane and vertical wall, columns, pipes and other penetrations including cracks and control joints to be coated with elastoguard paint.

APPLICATION GUIDELINE & INSTRUMENT FOR USE:

a) Brush, Roller & Others

Volume of Thinner	5-10%
Recommended Thinner	Pure water

b) Air Spray

Volume of Thinner	10-15%
Recommended Thinner	Pure water

c) Airless Spray

Volume of Thinner	NA
Recommended Thinner	NA

d) Cleaning Solvent

Pure water