

HYDROBIT RB15

Highly Rubberized Cold Applied Bituminous Coating

Description:

HYDROBIT RB15 is a superior quality, cold applied, water based highly rubberized, flexible bitumen liquid applied membrane. It is a mix of selected bitumen emulsified with water and the addition of special additives, to give an easy applied protective coating. Once dries the product gives a firm, high build flexible, jointless waterproofing and protective coating.

HYDROBIT RB15 is suitable for the treatment of concrete, metal, roofing and other similar surfaces whether flat, sloping or vertical.

Applications:

- Can be used for general waterproofing applications.
- Waterproofing for wet areas such as kitchens and bathrooms.
- Damp proofing of cement sheets, facades, etc.
- Cement pipes and metal. Protection against corrosion.
- Waterproofing coat for concrete footings and retaining walls.
- For maintenance of roofs including light weight screed, bitumen sheets, asbestos, slate, built up felt, etc.
- Acts as a vapor/salt barrier for exterior walls behind granite, marble, cladding, curtain walls, etc.
- To provide waterproofing separation layer between screed flooring.

Advantages:

- High build high solid liquid applied membrane
- Vapour permeable allows substrate to breathe.
- Reduced chloride penetration.
- Excellent resistance to chemicals.
- Solvent free and cold applied
- Once dries it give high flexible coating and can accommodate structure movement.

- Easy application due to paintable consistency.
- Excellent adhesive to most building surfaces.
- Superior protection for underground concrete against salty water.
- Can be used to gutters protection against acid.
- Can be used as a high quality waterproofing system for wet areas as in kitchen and bathroom.

Instructions for Use:

Surface Preparation:

All surfaces should be sound, clean, dry and free from loose material, efflorescence, laitance, curing compounds, dirt, oil and grease.

Cut and reseal blisters in asphalt or roofing. Remove chippings other than those that form the surface of mineralized felt. Porous surfaces should be primed using HYDROBIT diluted 1:4 with clean water. Old concrete and steel must be structurally sound prior to application.

Mixing:

HYDROBIT RB15 is a single component ready to use emulsion. Shake the barrel well to mix any settled material prior to application.

Application:

HYDROBIT RB15 can be applied with a roller, trowel, brush or a spraying machine. It is recommended to apply two coats in case of roller or brush applications. Second coat should be applied at right angle to the first coat. Minimum rate of spreading for each coat should be at a rate from 3 to 5 m² per liter per coat.

HYDROBIT RB15 may be applied to damp but not wet surfaces. Dampen brushes before and occasionally during use to avoid clogging and to ensure ease application. During hot, dry weather application may be assisted by dampening the surfaces which to be treated.

HYDROBIT RB15

When subsequent coats are applied, each coat should be completely dry before the next coat in order to avoid possible air bubbles due to evaporation of water in the subsequent coat.

To provide a good key to tiles fixing on top of screed, plastering, or for protection against foot traffic, spread the second coat while it is still tacky with clean sand.

HYDROBIT RB15 can be applied on several kind of surfaces such as concrete, blocks, brick, corrugated sheets, asbestos, zinc, steel, etc.

For waterproofing the underground structures, such as footings, HYDROBIT RB15 can be applied into green concrete immediately after removing the shutter. The applied coat will act as an effective curing membrane to the concrete. Apply the second coating once the first coat is dry. Backfill once the final coat is totally dry.

HYDROBIT RB15 can be applied as an adhesive to fix insulation boards such as cork and polystyrene to the concrete.

Standards:

HYDROBIT RB15 conforms to:

- ASTM D1187, D2939, D1227
- BS 8102

TECHNICAL PROPERTIES

Solid Contents	: 65%
Rubber Content	: 15%
Specific Gravity	: 1.15 @ 25°C
Service Temp.	: -15°C to + 85°C
Flexibility	: 200%
Flashpoint	: Non flammable
Drying Time	: 6 to 8 hours per coat @ 25°C
Appearance	: Dark black/brown coating. Cures to a hard tack free finish.
Chemical Resist.	: Excellent resistance to aqueous groundwater salt solutions, mild detergent, acids and alkalis

Packaging:

HYROBIT RB15 is available in 20 liter pails and 200 liter barrels.

Coverage:

HYDROBIT RB15 achieves coverage of 2 to 4 square meters per liter @ 2 coats.

Storage:

HYDROBIT RB15 to be stored in original packing in dry conditions away from direct sunlight and high humidity levels.

Shelf Life:

HYDROBIT RB15 can be utilized within 12 months of production date if stored in proper conditions in unopened original packing.

Cleaning:

Clean all tools with clean water before product hardens.

Health and Safety:

- Use goggles and gloves during application. Do not breathe the vapor of the product. Use only in well ventilated areas.
- Avoid contact with eyes or skin.
- In case of eyes contact, clean immediately with plenty of clean water and seek medical care.

MATEX Rev.02-1215

This technical data sheet is not considered as local building codes. It shall be used as general reference for the product, based on our current knowledge and experience. However the company do not accept any liability arising from the use of its products as it has no direct control on how and where the product is applied.

